




# 4636 YELLOW FAST DRY LATEX TRAFFIC MARKING PAINT

Low VOC - Lead Free Yellow

Product Description				Recommended Uses			
<p><b>4636 FAST DRY YELLOW LATEX TRAFFIC MARKING PAINT</b> is 100% latex acrylic (waterborne), designed for fast drying and quick turn around time. This is the best product to use for night striping and under adverse conditions.</p> <ul style="list-style-type: none"> <li>Formulated to Meet <b>IDOT 1095.02 Specification</b></li> <li>Formulated for Brush, Spray, or Roller</li> <li>Fastest Dry Time for Quick Turn Around.</li> </ul>				<p>This product has been designed for painting centerlines, edgelines, curbs, and auxiliary markings of highways, runways, running tracks, medians, parking lots, traffic aisles, etc.</p> <p>Use on concrete, asphalt, and brick. Exterior and Interior. This latex marking paint is considered to be the best product for use over freshly applied sealcoat or asphalt. <i>It is not recommended for restriping of previously striped lines.</i> Available in Yellow, White, Blue, Red, and Black.</p>			
Performance Characteristics				Product Characteristics			
Formulated to Meet <b>IDOT 1095.02 Specification</b>				<p>Vehicle Type: Acrylic Latex Polymer</p> <p>Viscosity: 83 to 98 Ku</p> <p>Weight Solids: 73.00% minimum</p> <p>Volume Solids: 50.00% - 54.00%</p> <p>Density (Weight per Gallon): 12.69 ± 0.20 lbs/gal</p> <p>VOC (minus exempts): 101 g/L</p> <p>VOC (with exempts): 67 g/L</p> <p>Dry time: No-Pick-Up: 5 – 10 minutes Dry Through: 10 – 15 minutes <i>(Note: Applied film thickness, relative humidity and temperature will affect dry time)</i></p> <p>Shelf Life: 12 months if unopened and stored in a cool area.</p> <p><i>This product does not contain mercury, lead, hexavalent chromium, toluene, chlorinated solvents, hydrolysable chlorine derivatives, or carcinogens as defined in 29 CFR 1910.1200.</i></p>			
Test Description	Test Method	Requirements	Results				
Color (yellow)	IDOT 1095.02 Fed. Std. 595 #33538	Pass	Pass				
Reflectance	IDOT 1095.02	50% minimum	Pass				
Fineness of Grind	ASTM D1210	3 Hegman min.	Pass				
Dry Time No-Pick-Up	ASTM D711	10 minutes max.	Pass				
Dry Time Dry Through	ASTM D1640	15 minutes max.	Pass				
Flexibility	TT-P-1952D	Pass	Pass				
Freeze-Thaw Resistance	TT-P-1952D	3 cycles	Pass				
Accelerated Package Stability	TT-P-1952D	<10 Ku change	Pass				
Water Resistance	TT-P-1952D	Pass	Pass				
Storage Stability	IDOT 1095.02	<5 Ku change	Pass				
Dry Opacity	IDOT 1095.02	0.97 minimum	Pass				
<p><i>Note: These results in Performance &amp; Product Characteristics represent actual control values when tested under laboratory conditions. To the best of our knowledge, the above technical data is true and accurate at the date of issuance but is subject to change without prior notice.</i></p>							
<p>The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. <b>HOWEVER, RAE PRODUCTS &amp; CHEMICALS CORPORATION MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.</b> UNDER NO CIRCUMSTANCES SHALL RAE PRODUCTS &amp; CHEMICALS CORP. BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF RAE PRODUCTS &amp; CHEMICALS CORP. FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY RAE PRODUCTS &amp; CHEMICALS CORP. SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER.</p> <p><b>CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!</b> BEFORE using this product it is essential that the "Material Safety Data Sheet" describing the product as well as the "Product Label" be reviewed. If your company does not have such information or has any questions, contact <b>RAE Products at 1-708-396-1984</b> or refer to data at <a href="https://rae-products.com">https://rae-products.com</a></p>							

# 4636 YELLOW FAST DRY LATEX TRAFFIC MARKING PAINT

Low VOC - Lead Free Yellow

Preparation	Application							
<p>The surface to be painted must be dry, free of grease and oil and brushed free of loose dirt. Striping paints will not adhere to unclean surfaces. Application equipment must be clean from all</p>	<p>Mix paint thoroughly before using. Surfaces should be clean and free from dirt and debris. Newly sealed or asphalted surfaces should be allowed to cure before application. Paint only in dry weather with no forecast for rain. May be applied by a spray machine, roller or brush.</p>							
Thinning	<p>Application Rates: Apply at 15 mils. wet , 7.5 mils dry Coverage: Approx. 16 gallons will stripe a 4-inch line one mile.</p> <p>Glass beads can be broadcast or mixed into paint at a rate of 4 - 6 pounds of beads per gallon. If spraying, do not mix beads directly into paint.</p>							
<p>Thinning is normally not required, but a small amount of water may be added if needed. <i>Add water sparingly!</i> Diluting with water can reduce paint viscosity rapidly. DO NOT add gasoline, oil or any other petroleum-based products to waterborne paints.</p>								
Drying Times	Application Conditions							
<p>Dry times are dependent upon weather conditions. The warmer the temperature, the faster the paint will cure. Direct sunlight will speed up dry times. For this product, a basic drying schedule is:</p> <p style="text-align: center;">10 min. (walk on) - 20 min. (drive on)</p> <p><i>Note: changes in weather conditions (ie. temp. dropping after application, cold surface temp.) can delay above cure times drastically.</i></p>	<p>Recommended application conditions: Apply between 40°F minimum and 90 °F and at least 5 °F above dew point with a relative humidity below 85%. Apply at surface and ambient temperatures of 50°F and above. Temperatures should remain above 50°F for a 24 hour period.</p>							
	Application Equipment							
Safety Precautions	<p><b>Spray Equipment:</b> The use of stainless steel spray equipment is strongly encouraged, due to the fact that an alkaline paint will “surface shock” when exposed to mild metals. Only stainless steel or plastic spray equipment should be used. Straining the paint when using spray equipment is ALWAYS recommended.</p> <p><b>Airless Sprayers:</b> Use pressure between 1500-2000 psi - with tip size between .015” - 0.19” (note: use the lowest pressure necessary to achieve a flat edge-line)</p> <p><b>Brush:</b> Use Nylon/Polyester Natural Bristle</p> <p><b>Roller:</b> Use 3/8” Shed-resistant cover with phenolic core</p>							
<p><b>Always refer to the MSDS for Handling and Hazard conditions.</b> Keep away from open flame. Avoid prolonged or repeated contact with skin. Avoid breathing of vapors or spray mist. Do not take internally. Close container after each use. Wear respirator, eye protection and protective clothing when handling.</p> <div style="display: flex; justify-content: space-around; align-items: center;">  <table border="1" data-bbox="532 1472 740 1640"> <tr><td>HEALTH</td><td>1</td></tr> <tr><td>FLAMMABILITY</td><td>0</td></tr> <tr><td>PHYSICAL HAZARD</td><td>0</td></tr> <tr><td>PERSONAL PROTECTION</td><td>X</td></tr> </table> </div>		HEALTH	1	FLAMMABILITY	0	PHYSICAL HAZARD	0	PERSONAL PROTECTION
HEALTH	1							
FLAMMABILITY	0							
PHYSICAL HAZARD	0							
PERSONAL PROTECTION	X							
<p>The following supersedes any provision contained in the forms, letters and papers of your company. This product is designed and intended for professional application only. All products should be thoroughly tested under application conditions prior to use. The information contained herein is believed to be reliable. <b>HOWEVER, RAE PRODUCTS &amp; CHEMICALS CORPORATION MAKES NO WARRANTY CONCERNING THIS PRODUCT, WHETHER EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.</b> UNDER NO CIRCUMSTANCES SHALL RAE PRODUCTS &amp; CHEMICALS CORP. BE LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL, OR ANY OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY, OR ANY OTHER LEGAL THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. THE SOLE REMEDY OF THE BUYER AND THE SOLE LIABILITY OF RAE PRODUCTS &amp; CHEMICALS CORP. FOR ANY CLAIMS SHALL BE LIMITED TO THE BUYER'S PURCHASE PRICE OF THE PRODUCT WHICH IS THE SUBJECT OF THE CLAIM OR THE AMOUNT ACTUALLY PAID FOR SUCH PRODUCT, WHICHEVER IS LESS. TECHNICAL ADVICE FURNISHED BY RAE PRODUCTS &amp; CHEMICALS CORP. SHALL NOT CONSTITUTE AN EXPRESS WARRANTY, WHICH IS EXPRESSLY DISCLAIMED. ALL TECHNICAL ADVICE GIVEN IS ACCEPTED AT THE RISK OF THE BUYER.</p> <p><b>CAUTION: DANGER! FLAMMABLE! VAPORS MAY CAUSE FLASH FIRE. VAPOR HARMFUL. HARMFUL OR FATAL IF SWALLOWED. INJURIOUS TO EYES. KEEP OUT OF THE REACH OF CHILDREN!</b> BEFORE using this product it is essential that the “Material Safety Data Sheet” describing the product as well as the “Product Label” be reviewed. If your company does not have such information or has any questions, contact <b>RAE Products at 1-708-396-1984 or refer to data at <a href="https://rae-products.com">https://rae-products.com</a></b></p>								